

Glass	COE	Annealing (°F)	Strain (°F)	Softening (°F)	Working (°F)	Source
Soft						
ASK (Arrow Springs Kugler)	104	920-970F	840F	1030F	1400F	Arrow Springs
Bullseye	90	960F	820F	-	-	Arrow Springs
	90	980F	750F	-	-	Jim Kervin
trans	90	990F	920F	1250F	-	EvenHeat
opal	90	935F	865F	1270F	-	-
goldpink	90	882F	820F	1180F	-	-
Caliente (Uroburos)	96	-	-	-	-	-
CR (C&R Loo)	96	-	-	-	-	-
Creation is Messy (CiM)	104	-	-	-	-	Kathy (CiM)
Cirrus	104	970-1040F	-	-	-	-
Peacock Green	104	1050F	-	-	-	-
Gelly's Sty	104	950F	-	-	-	-
Ginger	104	1010F	-	-	-	-
Celadon	104	1030F	-	-	-	-
Butter Pecan	104	1050F	-	-	-	-
Bordello	104	940F	-	-	-	-
Leaky Pen	104	980F	-	-	-	-
Halong Bay	104	1070F	-	-	-	-
CiM Messy 96	96	-	-	-	-	-
Czech	104	960-1000F	-	-	-	tri
Soda	103	850-900F	-	-	-	-
Lead, Opaque	95	850-900F	-	-	-	tri
Lead, Transparent	95	850-900F	-	-	-	tri
Lead, Shampoo	95	850-900F	-	-	-	tri
Double Helix	104	-	-	-	-	-

Easy Flow		132	745F	694F	-	-
Effetre		104	920-968F	840F	1100F	1400F ArrowSprings
		104	970F	680F	-	- Jim Kervin
Gaffer		96	905-932F	824F	-	- Gaffer
GG Glass, cane		96	-	-	-	-
GNA Antique Sheet		90	-	-	-	-
Kinari		125-130	-	-	-	-
	A (Lead)		-	-	-	- Kinari
	B (Soda)		-	-	-	- Kinari
	C (Soda)	128	430C	-	480-520C	- Kinari
Kugler		93	-	-	-	- Olympic
	Trans	91-95	-	-	-	- C&R Loo
	Opaque	89-93	-	-	-	- C&R Loo
Lauscha		95-105	900F	-	-	- Jim Kervin
		95-105	980F	750F	-	- Carol Anne
Pi Glass		96	-	-	-	-
Q-Colors by Reichenbach		91-94	-	-	-	-
R4 Glass		104	980F	-	-	- R4 Studios
Reichenbach		91-94	490-520C	-	-	- Hot Bead Box
Satake		113-120	870F	-	-	- Jim Kervin
	Lead	120	890F	750F	-	- Arrow Springs
	Lead	120	890F	-	-	- Satake
	Soda	113	890F	-	-	- Satake

Schott		-	-	-	-	-	-
Spectrum	Sheet	96	950F	700F	-	-	- Jim Kervin
Spruce Pine *83		91-92	-	-	-	-	-
Spruce Pine *87		96	-	-	-	-	-
System 96		96	-	-	-	-	-
Uroboros		90	-	-	-	-	-
	trans		977F	910F	-	-	- Uroboros
	opals		954F	875F	-	-	- Uroboros
		96	963F	898F	-	-	- Uroboros
	(trans)	96	960F	900F	-	-	- Arrow Springs
	(opal)	96	960F	860F	-	-	- Arrow Springs
Vetrofond		104	920-968F 878-970F	840F -	1100F -	1400F	Arrow Springs - Hot Bead Box
Wasser	Urobuos sheet	90	950F	650F	-	-	- Jim Kervin
Weisenthal	(old)	97-99	-	-	-	-	- C&R Loo
	(new)	89-93	-	-	-	-	- C&R Loo
Zimmerman		94	-	-	-	-	-
Zimmerman, Kugler		89-93	-	-	-	-	-

Boro

Boromax	Boromax	-	1050F	950F	-	-	- Arrow Springs
Duran	Duran	32	-	-	-	-	-
Glass Alchemy			1050F	950F	-	-	- ???

		33.2 +/- 2	565-1050F	840F	1200F	1700F Arrow Springs
Kimax		33	-	-	-	-
Kimball		33	-	-	-	-
Momkas		30-33	-	-	-	-
NorthStar		33.2 +/- 2	565-1050F	840F	1200F	- Arrow Springs
Precision	Precision	30-33	-	-	-	-
Pyrex	Pyrex	32	1058F	950F	-	- Jim Kervin
Simax	Simax	33	-	-	-	-

Other:

Window Glass		84-87	1150F	850F	-	- Jim Kervin
Armstrong Float		82 +/- 3	-	-	-	-